



## No. 15 Asphalt Felt – ASTM D 226

### Product Description:

**TRI-BUILT No.15 – ASTM D 226** is a widely accepted underlayment product that is manufactured from superior quality organic felt that is saturated with asphalt. Line markings are placed on the top surface at 2”, 8 ½”, 11 5/16”, and 17” from each side of the sheet.

### Product Use:

**TRI-BUILT No.15 – ASTM D 226** underlayment is applied over the roofing deck before installation of asphalt shingles. This product is highly recommended as an underlayment for architectural shingles and is not recommended for 20 year 3 tab shingles.

### Technical Data:

ASTM D 226 Type I	
Width of roll	36”
Roof coverage per roll (min.)	432 sq ft
Mass of saturated felt roll (min.)	11.5 lbs/ 100 ft sq
Mass of asphalt saturant (min.)	6.2 lbs / 100 ft sq
Mass of desaturated felt	5.2 lbs / 100 ft sq
Max ash	10%
Average (min.) breaking strength	
Machine direction	30 lbf/in
Cross direction	15 lbf/in
Pliability at 77 degrees F when bend 90 degrees	½” radius
Max. loss on heating at 221 degrees F	4%

### Packaging:

Pallet Size	42” x 48”
Rolls per Pallet	25 - 4 square rolls
Pallets per Truck	36



## No. 30 Asphalt Felt – ASTM D 226

### Product Description:

**TRIBUILT No.30 – ASTM D 226** is a widely accepted underlayment product that is manufactured from superior quality organic felt that is saturated with asphalt. Line markings are placed on the top surface at 2”, 8 ½”, 11 5/16”, and 17” from each side of the sheet.

### Product Use:

**TRIBUILT No.30 – ASTM D 226** underlayment is applied over the roofing deck before installation of asphalt shingles. This product is highly recommended as an underlayment for architectural shingles and is not recommended for 20 year 3 tab shingles.

### Technical Data:

ASTM D 226 Type II	
Width of roll	36”
Roof coverage per roll	216 sq ft
Mass of saturated felt roll	26.0 lbs/ 100 ft sq
Mass of asphalt saturant	15.0 lbs / 100 ft sq
Mass of desaturated felt	10.0 lbs / 100 ft sq
Max ash	10%
Average (min.) breaking strength	
Machine direction	40 lbf/in
Cross direction	20 lbf/in
Pliability at 77 degrees F when bend 90 degrees	¾” radius
Max. loss on heating at 221 degrees F	4%

### Packaging:

Pallet Size	42” x 48”
Rolls per Pallet	25 - 2 square rolls
Pallets per Truck	36