



## No. 15 Asphalt Felt – ASTM D 4869

### Product Description:

**TRIBUILT No.15 – ASTM D 4869** is a widely accepted underlayment product that is manufactured from organic felt and is saturated with asphalt.

### Product Use:

**TRIBUILT No.15 – ASTM D 4869** underlayment is applied over the roofing deck before installation of asphalt shingles. It is recommended for use with 20 and 25 year asphalt shingles.

### Technical Data:

ASTM D 4869 Type I	
Width of roll	36"
Roof coverage per Roll	432 sq ft
Mass of saturated felt roll	8.0 lbs/ 100 ft sq
Mass of asphalt saturant	4.0 lbs / 100 ft sq
Mass of desaturated felt	4.0 lbs / 100 ft sq
Saturation by weight (min)	100%
Saturation efficiency (min) by weight	75%
Breaking strength at 77F (min)	
Machine direction	30 lbf/in
Cross direction	15 lbf/in
Pass 4 hour liquid transmission water test	YES
Pliability at 77F when bend 90 degrees	½" radius

### Packaging:

Pallet Size	42" x 42"
Rolls per Pallet	30 - 4 square rolls
Pallets per Truck	44

Note: Special runs of 400 sq.ft. rolls do not meet ASTM 4869 Type I



## No. 30 Asphalt Felt – ASTM D 4869

### Product Description:

**TRIBUILT No.30 – ASTM D 4869** is a widely accepted underlayment product that is manufactured from organic felt and is saturated with asphalt. Line markings are placed on the top surface at 2", 8 ½", 11 5/16", and 17" from each side of the sheet.

### Product Use:

**TRIBUILT No.30 – ASTM D 4869** underlayment is applied over the roofing deck before installation of asphalt shingles. This product is highly recommended as an underlayment for architectural shingles and is not recommended for 20 year 3 tab shingles.

### Technical Data:

ASTM D 4869 Type I	
Width of roll	36"
Roof coverage per roll	216 sq ft
Mass of saturated felt roll	13.0 lbs/ 100 ft sq
Mass of asphalt saturant	6.0 lbs / 100 ft sq
Mass of desaturated felt	5.0 lbs / 100 ft sq
Saturation by weight (min)	100%
Saturation efficiency (min) by weight	75%
Breaking strength at 77F (min)	
Machine direction	30 lbf/in
Cross direction	15 lbf/in
Pass 4 hour liquid transmission water test	YES
Pliability at 77F when bend 90 degrees	½" radius

### Packaging:

Pallet Size	42" x 42"
Rolls per Pallet	25 - 2 square rolls
Pallets per Truck	32